

TECHNICAL INFORMATION

COPY LASERJET 70 U-A1110-WK50

BASE PAPER

White, woodfree machine finished printing paper for laser-copy application.

Typical technical values

Grammage	70	g/m ²	ISO 536
Caliper	90	μ	ISO 534
Tensile strength (machine direct)	4,8	kN/m	ISO 1924
Tensile strength (cross direct)	1,8	kN/m	ISO 1924

ADHESIVE

Acrylic waterbased, permanent adhesive for general purpose application.

Typical technical values

Quick stick(PE)	8 N	FINAT FTM 9
Peel Adhesion 180° (PE)	Paper Tear (PT)	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	-40 °C - +70 °C	

BACKING

White, wood-free one side siliconised kraft paper.

Typical technical values

Basis Weight	51	g/m ²	ISO 536
Caliper	51	μ	ISO 534
Tensile strength (machine direct min.)	4,3	kN/m	ISO 1924
Tensile strength (cross direct min.)	1,6	kN/m	ISO 1924

Adhesive performance

This adhesive is characterized by high initial tack and excellent adhesion on a wide variety of dry surfaces including cardboard and corrugated cardboards. It shows excellent adhesion on slightly chilled surfaces. The composition, temperature and contamination of the surface can affect the adhesion so preliminary tests are recommended.

Shelf life

2 years

Storage conditions

23+/-2°C, 50+/-5% RH

Warranty: All statements and recommendation about BUDAVAL products are based on our most-up-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the product are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

04/2016