

PVC TRANSPARENT GLOSS 90 –A6030-WG80**Preliminary data sheet****FACE MATERIAL**

Transparent, PVC film.

Typical technical values:

Basis Weight	116	g/m ²
Caliper	91	µm
Gloss 60°	≥80	

ADHESIVE

Water based APEO free adhesive designed for film application.

Typical technical values

Initial Tack (on glass)	9 N	FINAT FTM 9
Adhesion 180° (on glass)	9 N	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	-20 °C - +70 °C	

BACKING

White, wood-free one side siliconised. glassine backing paper.

Typical technical values

Basis Weight	78	g/m ²	ISO 536
Caliper	68	µ	ISO 534
Tensile strength MD	≥6,7	kN/m	ISO 1924
Tensile strength CD	≥3,3	kN/m	ISO 1924

Adhesive performance

This adhesive is characterized by good initial tack and adhesion.

Application and usage

It is recommended for product e.g. labeling toiletries cosmetics and drinks.

Printability

Special inks should be used that are designed for nonabsorbent surfaces.

Shelf life

2 years

Storage conditions

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

07./2019.