

VELLUM T BP -A 4024 - WG65

FACE MATERIAL

Wood-free, machine formed, white paper.

Typical technical values

Basis Weight	70+/-3	g/m ²	ISO 536
Caliper	69+/-5	μ	ISO 534
Tensile strength CD	≥2,3	kN/m	ISO 1924
Tensile strength MD	≥4,5	kN/m	ISO 1924
Brightness D65	106	%	ISO 2470
Opacity	88	%	ISO 2471
CIE Whiteness	150	%	ISO 11475

ADHESIVE

Removable, water-based acrylic adhesive.

Typical technical values

Initial Tack (on PE)	2 N	FINAT FTM 9
Adhesion 180° (on PE)	1,0 N	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	+5 °C - +60 °C	

BACKING

White, wood-free, transparent glassine backing paper. One side siliconised.

Typical technical values

Basis Weight	58	g/m ²	ISO 536
Caliper	49	μ	ISO 534
Tensile strength MD	≥5,1	kN/m	ISO 1924
Tensile strength CD	≥2,1	kN/m	ISO 1924

Adhesive performance

The adhesive is characterized by good initial tack. This adhesive is not suitable for labelling rough, curved surfaces, cardboard and also PVC surfaces, which contain plasticizers. The composition, temperature and contamination of the surface can affect the adhesion so preliminary tests are recommended.

Application and usage

This is an universal label-paper for product labeling, marking and logistic labeling, where the basic information is printed with classical printing technologies and the variable information is printed at the end-users. Suitable for thermal transfer printing with wax and wax/resin ribbons.

Printability

This material has very good printability in all classical printing processes (flexography, letterpress, offset) and also has very good printability in variable information printing (inkjet, laser, thermal transfer).

Shelf life

1 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

03/2020.