

VELLUM T OPAQUE –A1110- HG65

FACE MATERIAL

Wood-free, machine formed, white paper with back side grey coloured.

Typical technical values

Basis Weight	75	g/m ²	ISO 536
Caliper	73	μ	ISO 534
Tensile strength CD	≥2,3	kN/m	ISO 1924
Tensile strength MD	≥4,5	kN/m	ISO 1924

ADHESIVE

General-purpose strong water-based acrylic adhesive.

Typical technical values

Initial Tack (on glass)	12 N	FINAT FTM 9
Adhesion 180° (on glass)	Paper tear (PT)	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	-40 °C - +70 °C	

BACKING

Yellow, wood-free, transparent glassine backing paper. One side siliconised.

Typical technical values

Basis Weight	57	g/m ²	ISO 536
Caliper	49	μ	ISO 534
Tensile strength MD	≥5,0	kN/m	ISO 1924
Tensile strength CD	≥2,6	kN/m	ISO 1924

Adhesive performance

This adhesive is characterized by high initial tack and excellent adhesion on a wide variety of dry surfaces including cardboard and corrugated cardboards. It shows excellent adhesion on slightly chilled surfaces. The composition, temperature and contamination of the surface can affect the adhesion so preliminary tests are recommended.

Application and usage

This is an universal label-paper for product labeling, marking and logistic labeling, where the basic information is printed with classical printing technologies and the variable information is printed at the end-users. Suitable for thermal transfer printing with wax and wax/resin ribbons.

Printability

This material has very good printability in all classical printing processes (flexography, letterpress, offset) and also has very good printability in variable information printing (inkjet, laser, thermal transfer).

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.
03/2020.