

BOPP WHITE PEARL BTC 60 –A6020 - WG65

FACE MATERIAL

White/ pearl colour biaxially orientated, top coated, polypropylene film. Films should be allowed to reach operating room temperatures for 24 hours before use.

Typical technical values:

Basis Weight	42	g/m ²	ISO 536
Caliper	60	μ	ISO 534

ADHESIVE

Typical technical values

Initial Tack (on glass)	6 N	FINAT FTM 9
Adhesion 180° (on glass)	6 N	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	-20 °C - +70 °C	

BACKING

White, wood-free transparent glassine backing paper. One side siliconised.

Typical technical values

Basis Weight	58	g/m ²	ISO 536
Caliper	49	μ	ISO 534
Tensile strength MD	≥5,1	kN/m	ISO 1924
Tensile strength CD	≥2,1	kN/m	ISO 1924

Adhesive performance

This adhesive is characterized by good initial tack and adhesion. Not suitable for labelling rough surfaces plasticised PVC surfaces, greasy surfaces.

Application and usage

It is recommended for product e.g. labeling toiletries cosmetics and drinks.

Printability

This material has very good printability in all printing processes as flexography, letterpress, offset, screen, Special inks should be used that are designed for nonabsorbent surfaces.

Shelf life of the laminate

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

09/2019