



## PET SILVER GLOSS TC50-A6020-WG65

### FACE MATERIAL

Al-metallised top coated, glossy polyester film.

#### Typical technical values

Basis Weight	61+/-4	g/m <sup>2</sup>	ISO 536
Caliper	46+/-4	μ	ISO 534
Tensile Strength MD	≥150	Mpa	GB/T1040

### ADHESIVE

#### Typical technical values

Initial Tack ( on glass )	6 N	FINAT FTM 9
Adhesion 180° (on glass)	6 N	FINAT FTM 1
Application temperature min.	+5 °C	
Service temperature	-20 °C - +70 °C	

### BACKING

White, wood-free, transparent glassine backing paper. One side siliconised.

#### Typical technical values

Basis Weight	58	g/m <sup>2</sup>	ISO 536
Caliper	49	μ	ISO 534
Tensile strength MD	≥5,1	kN/m	ISO 1924
Tensile strength CD	≥2,1	kN/m	ISO 1924

### Adhesive performance

This adhesive is characterized by good initial tack and adhesion. Not suitable for labelling rough surfaces plasticised PVC surfaces, greasy surfaces.

### Printability

This face material has glossy top coating layer, which gives good printing performance across a wide variety of all conventional printing processes. ( flexo, letter press, offset, silk screen printing) However, exact ink and foil system should be recommended by your ink supplier.

### Shelf life

2 years

### Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.  
10/2019.