

PET SILVER VOID TC50 –A5010 - WG65

FACE MATERIAL

Al-metallised top coated, polyester film with tamper proof print"VOID"

Typical technical values

Basis Weight	70	g/m ²	ISO 536
Caliper	51	μ	ISO 534
Tensile Strength MD	20	daN/mm ²	ASTM D882

ADHESIVE

General-purpose strong water-based acrylic adhesive.

Typical technical values

Initial Tack (on glass)	12 N/Foil Tear	FINAT FTM 9
Adhesion 180° (on glass)	12 N/Foil Tear	FINAT FTM 1
Application temperature min.	min.+5 °C	
Service temperature	-40 °C - +70 °C	

BACKING

White, wood-free transparent glassine backing paper. One side siliconised.

Typical technical values

Basis Weight	58	g/m ²	ISO 536
Caliper	49	μ	ISO 534
Tensile strength MD	≥5,1	kN/m	ISO 1924
Tensile strength CD	≥2,1	kN/m	ISO 1924

Adhesive performance

Generally using for security labels or products. The face material cannot be removed without permanently damaging the label. The print „VOID" will remain on the surface of labelled product.

We don't recommend to make a series of copies, because the printer will heat up and there will certainly be a problem not only with top coat and print but also with the PET-film itself, because the film will get distorted.

Preliminary tests are recommended due to different substrates and applications.

Shelf life

2 years

Storage

23±2 °C, 50±5 % RH

Warranty: All statements and recommendations about BUDAVAL products are based on our most up-to-date knowledge, experience and tests believed to be reliable but do not constitute a guarantee or warranty. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the product. This technical information sheet replaces all earlier ones. All information subject to change without notice.

09/2019.